

DECOPOT LTD

mail order potter's supplies

	New 2017	New 2017	New 2017	New 2017	New 2017
Partnumber	BODYRBSW	BODYWBSW	BODYCRSW	BODYWRBS	BODYTERB
NAME	Red-Brown Stoneware - 202	Wood-Brown Stoneware - 208	Cream Stoneware - 301	Warm-Buff Sculpture - 201	Red-Brown Terracotta - 203a
<i>Similar to</i>	<i>Standard Stoneware</i>		<i>White Stoneware</i>		<i>Primo Red</i>
Recommended for	Throw and Build	Throw and Build	Throw and Build	Slab and Build	Slab, Build & Throw
Body Type	Smooth body	Smooth body	Smooth body	Coarse grog body	Smooth body
Potter's notes	<i>"Smooth, plastic, well behaved general purpose clay. Superb throwing characteristics. Stands up well - Integrity. Holds moisture well."</i>	<i>"Slightly more compact. Throws extremely well. Excellent results with flahing. Great for turning."</i>	<i>"Throwers Delight! Excellent turning and great stand-up. A general purpose clay for small to very large pots. Flashes well. Slower dehydration and takes attachments well."</i>	<i>"Ideal for medium to large sculptural and architectural works. Flashes well"</i>	<i>"Very good to throw... it feels like a stoneware on the wheel. Flashes well. Consistent slow drying enabling it to take attachments well."</i>
Shrinkage & Absorption	@1200C Shrinkage 13% & Absorption 4.9%	@1160C Shrinkage 13% & Absorption 3.6%	@1260C Shrinkage 11% & Absorption 3%	@1200C Shrinkage 10% & Absorption 4.6%	@1185C Shrinkage 13% & Absorption 1.2%
Temperatures	Bisque 950 – 1000C. Glaze 1160 – 1280C	Bisque 950 – 1000C. Glaze 1160 – 1250C	Bisque 950 – 1000C. Glaze 1160 – 1280C	Bisque 950 – 1000C. Glaze 1160 – 1280C	Bisque 950 – 1000C. Glaze 1100 – 1240C
10kg Bag Price	\$18.00	\$21.50	\$22.50	\$23.50	\$17.00
20x 10kg bags + Price	\$14.50	\$17.50	\$18.00	\$19.00	\$13.50